



NR / SBR Rubber Sheet

NR / SBR rubber sheet black color with no insertion and with one insertion



- Raw Material:** high-grade black NR / SBR
Reinforcement: 0 or 1 insertion
Surface: booth sides plate finish
Hardness: 65 ± 5 Shore A
Tensile strength: 3.0 MPa
Elongation: 250%
Temperature: - 30°C to + 70°C (-22°F to 158°F)
Specific Gravity: 1.5g / cm³
Weather resistance: satisfactorily resistant
UV resistance: satisfactorily resistant
Oil resistance: non resistant
Gasoline and fuel resistance: non resistant
Acid and solvents resistance: non resistant
Abrasion resistance: good resistance
Strong bases: resistant
Impact resistance: resistant

Thickness		Width		Length		Nr. of insertions
mm	inch	m	feet	m	feet	
0,8	1/32"	1,0	3.28	20	65.62	0
1,6	1/16"	1,0	3.28	20	65.62	0
2,4	3/32"	1,0	3.28	20	65.62	0
3,2	1/8"	1,0	3.28	20	65.62	0
4,8	3/16"	1,0	3.28	20	65.62	0
6,4	1/4"	1,0	3.28	20	65.62	0
7,9	5/16"	1,0	3.28	20	65.62	0
9,5	3/8"	1,0	3.28	20	65.62	0
12,7	1/2"	1,0	3.28	10	32.81	0

Thickness		Width		Length		Nr. of insertions
mm	inch	m	feet	m	feet	
0,8	1/32"	1,0	3.28	20	65.62	1
1,6	1/16"	1,0	3.28	20	65.62	1
2,4	3/32"	1,0	3.28	20	65.62	1
3,2	1/8"	1,0	3.28	20	65.62	1
4,8	3/16"	1,0	3.28	20	65.62	1
6,4	1/4"	1,0	3.28	20	65.62	1
7,9	5/16"	1,0	3.28	20	65.62	1
9,5	3/8"	1,0	3.28	20	65.62	1
12,7	1/2"	1,0	3.28	10	32.81	1

Construction characteristics and dimensions may be changed at any time without prior notice.

The data contained herein is information purposes only and does not enlarge, amend or imply any warranty other than provided by the manufacturer with the product. Any use of the product not in conformance with the manufacturer's instructions may be dangerous.

Only items in this catalogue are carried in stock. Some items are subjected to minimum quantities or sold only in multiples of standard quantities. Please refer to the price list or contact our commercial department.